



# COHERETM PLASTOMER 8102L

METALLOCENE POLYOLEFIN PLASTOMER

### DESCRIPTION

COHERETM Metallocene Polyolefin Plastomer (POP) 8102L is an ethylene-octene copolymers produced via solution polymerization using metallocene catalyst. It performs well in high performance LLDPE blown film applications with an excellent combination of toughness, hot tack, sealing and optical properties. It contains slip and antiblock additives.

### TYPICAL APPLICATIONS

Low temperature sealing layer for high value packaging (low SIT, seal through contamination, toughness improvement)

### TYPICAL PROPERTY VALUES

Revision 20211208

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	1.0	g/10 min	ASTM D1238
Density <sup>(1)</sup>	902	kg/m³	ASTM D1505
Mooney viscosity			
ML 1+4, 121 °C	20	MU	ASTM D1646
FORMULATION			
Slip agent	<input checked="" type="checkbox"/>	-	-
Anti block agent	<input checked="" type="checkbox"/>	-	-
MECHANICAL PROPERTIES <sup>(2)</sup>			
Tensile Strength at Break <sup>(3)</sup>	250	kgf/cm²	ASTM D638
Tensile Elongation at Break <sup>(3)</sup>	800	%	ASTM D638
Flexural Modulus (1% Secant)	840	kgf/cm²	ASTM D790
Tear Strength (Type C)	87	kgf/cm²	ASTM D624
Hardness			
Shore A (1 sec)	92	-	ASTM D2240
Shore D (1 sec)	40	-	ASTM D2240
OPTICAL PROPERTIES			
Haze	4	%	ASTM D1003
FILM PROPERTIES			
Tensile test film <sup>(4)</sup>			
stress at break MD	47	MPa	ASTM D882
stress at break TD	42	MPa	ASTM D882
elongation at break MD	600	%	ASTM D882
elongation at break TD	620	%	ASTM D882
1% secant modulus MD	68	MPa	ASTM D882
1% secant modulus TD	76	MPa	ASTM D882
Dart Impact F50 <sup>(4)</sup>	>1000	g	ASTM D1709
Elmendorf Tear Strength <sup>(4)</sup>			
MD	10	g/µm	ASTM D1922
TD	17	g/µm	ASTM D1922



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Sealing Initiation Temperature <sup>(4)</sup>	80	°C	SABIC method
<b>THERMAL PROPERTIES</b>			
Melting Point	105	°C	SABIC method
Glass Transition Temperature, T <sub>g</sub>	-31	°C	SABIC method

(1) Base resin density.

(2) Evaluated using compression molded sample.

(3) Crosshead speed: 500mm/min.

(4) Properties have been measured by producing 50 µm film with 2.5 BUR using 100% COHERE 8102.

## PROCESSING CONDITIONS

Typical processing conditions for COHERE™ 8102L are:  
Barrel temperature: 180 - 200°C, Blow up ratio: 2.0 - 3.0

## FOOD REGULATION

Please contact the local Sales / Technical representative for details.

## STORAGE AND HANDLING

The resin should be stored in a manner to prevent a direct exposure to sunlight and / or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions that may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.