

## Product Datasheet



## ExxonMobil™ HD 5290HLZ

(Legacy name: ExxonMobil™ HDPE HPA 020HDZ)

## High Density Polyethylene

## Product Description

ExxonMobil™ HD 5290HLZ is a high molecular weight HDPE resin, characterized by an excellent balance of rigidity, ESCR and impact strength.

## General

|                           |                                                                                                                                                                                                        |
|---------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Availability <sup>1</sup> | <ul style="list-style-type: none"> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> <li>Europe</li> </ul>                                                                                       |
| Additive                  | <ul style="list-style-type: none"> <li>Thermal Stabilizer: Yes</li> </ul>                                                                                                                              |
| Applications              | <ul style="list-style-type: none"> <li>Drainage Pipes</li> <li>Heavy Gauge Sheet</li> <li>Large Part Blow Molding</li> <li>Large Parts &amp; Containers (20 to 100 L) for non-food end uses</li> </ul> |
| Revision Date             | <ul style="list-style-type: none"> <li>04/03/2023</li> </ul>                                                                                                                                           |

| Resin Properties                                    | Typical Value (English)   | Typical Value (SI)      | Test Based On |
|-----------------------------------------------------|---------------------------|-------------------------|---------------|
| Density                                             | 0.952 g/cm <sup>3</sup>   | 0.952 g/cm <sup>3</sup> | ASTM D1505    |
| High Load Melt Index (190°C/21.6 kg)                | 9.0 g/10 min              | 9.0 g/10 min            | ASTM D1238    |
| Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)            | 0.35 g/10 min             | 0.35 g/10 min           | ASTM D1238    |
| Thermal                                             | Typical Value (English)   | Typical Value (SI)      | Test Based On |
| Vicat Softening Temperature                         | 259 °F                    | 126 °C                  | ASTM D1525    |
| Molded Properties                                   | Typical Value (English)   | Typical Value (SI)      | Test Based On |
| Tensile Modulus (0.20 in/min (5.0 mm/min))          | 150000 psi                | 1000 MPa                | ASTM D638     |
| Tensile Stress at 100%<br>2.0 in/min (50 mm/min)    | 2000 psi                  | 14 MPa                  | ASTM D638     |
| Tensile Strength at Yield<br>2.0 in/min (50 mm/min) | 3000 psi                  | 21 MPa                  | ASTM D638     |
| Elongation at Break<br>(2.0 in/min (50 mm/min))     | > 100 %                   | > 100 %                 | ASTM D638     |
| Environmental Stress-Crack Resistance               |                           |                         | ASTM D1693    |
| 10% Igepal                                          | 330 hr                    | 330 hr                  |               |
| 100% Igepal                                         | > 600 hr                  | > 600 hr                |               |
| Durometer Hardness (Shore D, 15 sec)                | 61                        | 61                      | ASTM D2240    |
| Impact                                              | Typical Value (English)   | Typical Value (SI)      | Test Based On |
| Notched Izod Impact Strength                        | 8.6 ft-lb/in <sup>2</sup> | 18 kJ/m <sup>2</sup>    | ISO 180/1A    |

## Legal Statement

This product is not intended for use in food contact application.

This product is not intended for use in medical applications and should not be used in any such applications.

## Processing Statement

The molded properties have been measured on compression molded sheets, prepared according to ASTM D4703 and ASTM D 638. ASTM D 638: Specimen type T1 / thickness 3 mm (118 mil); tensile modulus : speed of testing 5 mm/min (197 mil/min); tensile strength at yield and elongation at break: speed of testing 50 mm/min (1970 mil/min). ASTM D1693: Conditions B, F50, 10 % Igepal and 100 % Igepal

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Product Datasheet

**ExxonMobil**

ExxonMobil™ HD 5290HLZ  
High Density Polyethylene

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)

