



# LEXANT™ RESIN EX7681T

REGION EUROPE

## DESCRIPTION

LEXANT™ EX7681T resin is a highly UV stabilized 10 MFR polycarbonate, MVR of 10. Suitable for co-extrusion / cap layers. Exhibits low plate out and improved outdoor weathering on PC sheets.

## TYPICAL PROPERTY VALUES

Revision 20230725

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	70	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	120	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
THERMAL			
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
PHYSICAL			
Density	1.2	g/cm³	ISO 1183
Melt Volume Rate, MVR at 300°C/1.2 kg	10	cm³/10 min	ISO 1133
SHEET EXTRUSION			
Drying Temperature	100 – 110	°C	
Drying Time	2 – 3	Hrs	
Melt Temperature	220 – 250	°C	
Barrel - Zone 1 Temperature	240 – 280	°C	
Barrel - Zone 2 Temperature	240 – 280	°C	
Barrel - Zone 3 Temperature	220 – 240	°C	
Barrel - Zone 4 Temperature	220 – 240	°C	
Adapter Temperature	220 – 240	°C	
Die Temperature	245 – 290	°C	
Roll Stack Temp - Top	175 – 180	°C	
Roll Stack Temp - Middle	175 – 180	°C	
Roll Stack Temp - Bottom	175 – 180	°C	
PROFILE EXTRUSION			
Drying Temperature	100 – 110	°C	
Drying Time	2 – 3	Hrs	
Melt Temperature	180 – 200	°C	
Barrel - Zone 1 Temperature	165 – 185	°C	
Barrel - Zone 2 Temperature	170 – 190	°C	
Barrel - Zone 3 Temperature	175 – 195	°C	
Barrel - Zone 4 Temperature	180 – 200	°C	
Hopper Temperature	60 – 80	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Adapter Temperature	170 – 190	°C	
Die Temperature	180 – 200	°C	
Calibrator Temperature	60 – 100	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

