



SABIC® HDPE ICP5602

HIGH DENSITY POLYETHYLENE

DESCRIPTION

SABIC® HDPE ICP5602 is part of SABIC's high density polyethylene Industrial Container Product portfolio.

SABIC® HDPE ICP5602 is typically used for blow molding UN certified Tight Head drums, from 25 up to 220 liters. This food approved grade combines good processing performance with good stress crack resistance, stiffness and impact performance.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

Revision 20191018

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190 °C and 21.6 kg	2.3	dg/min	ISO 1133
Density ⁽¹⁾	956	kg/m ³	ISO 1183
MECHANICAL PROPERTIES ^{(1) (2)}			
Tensile test ^{(3) (4)}			
stress at yield	27	MPa	ISO 527-2
stress at break	40	MPa	ISO 527-2
strain at break	1000	%	ISO 527-2
tensile modulus	1100	MPa	ISO 527-2
Flexural test			
Flexural modulus	1350	MPa	ISO 178
Flexural strength	28	MPa	ISO 178
Izod impact notched			
at -30 °C	62	kJ/m ²	ISO 180/A
Hardness Shore D	62	-	ISO 868
ESCR (Strain Hardening), Gp	17	MPa	ISO 18488
ESCR (10% Igepal CO-630), F50	130	h	ASTM D1693B
THERMAL PROPERTIES			
Heat deflection temperature ^{(1) (2)}			
at 0.45 MPa (HDT/B)	83	°C	ISO 75-2
Vicat Softening Temperature ^{(1) (2)}			
at 10 N (VST/A)	128	°C	ISO 306
DSC test			
melting point	133	°C	ISO 11357-3
enthalpy change	210	J/g	ISO 11357-3

(1) Compression moulding of test specimen according to ISO 1872-2

(2) Conditioning of test specimen: temp. 23 °C, relative humidity 50 %, 24 hours

(3) Speed of testing: 50 mm/min

(4) Test specimen according to ISO 527-2 type 1BA, thickness 2 mm



ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.