







SABIC® HDPE M40055M

PROVISIONAL TECHNICAL DATA SHEET HIGH DENSITY POLYETHYLENE

DESCRIPTION

HDPE M40055M is a High Density Polyethylene specially developed for injection molding applications such as pallets and dust bins. HDPE M40055M exhibits high ESCR, good impact resistance, flowability and low warpage.

TYPICAL APPLICATIONS

M40055M is specially developed for Caps & Closures, Crates, Housewares, Industrial pails, Panels & Profiles, Sports, Leisure & toys.

TYPICAL PROPERTY VALUES			Revision 20211203
PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES (1)			
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	3.6	g/10 min	ISO 1133
at 190°C and 5 kg	11	g/10 min	ISO 1133
Density			
@23°C	955	kg/m³	ISO 1183
MECHANICAL PROPERTIES (2)			
Tensile modulus	1200	MPa	ISO 527
Charpy Notched Impact Strength (-30°C, Type 1,	Notch A) >3.5	kJ/m²	ISO 179

⁽¹⁾ Typical values: not to be construed as specification limits.

PROCESSING CONDITIONS

Recommended processing temperature: 180°C to 250°C

STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

⁽²⁾ Based on compression molded sheet.