



# SABIC® LDPE 2801H0W

## LOW DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® LDPE 2801H0W offers high production output with very good optical properties, as well as good stiffness toughness balance.

#### Application

SABIC® LDPE 2801H0W is typically used for high clarity collation shrink films, glossy automatic packaging printed films and deep freeze films. SABIC® LDPE 2801H0W can typically be used for food applications due to very low migration levels.

#### Film properties

Film properties have been measured at 30 µm film with a BUR of 3.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL PROPERTY VALUES

Revision 20211203

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Density	928	kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (MFR) at 190 °C and 2,16 kg	0.55	dg/min	ISO 1133
<b>OPTICAL PROPERTIES</b>			
Gloss (45°)	70	%	ASTM D2457
Haze	6	%	ASTM D1003
<b>FILM PROPERTIES</b>			
Impact strength	25	kJ/m	ASTM D4272
Tear strength TD	35	kN/m	ISO 6383-2
Tear strength MD	45	kN/m	ISO 6383-2
<b>Tensile test film</b>			
Stress at break MD	21	MPa	ISO 527-3
Modulus of elasticity TD	340	MPa	ISO 527-3
Yield stress TD	14	MPa	ISO 527-3
Stress at break TD	22	MPa	ISO 527-3
Yield stress MD	13	MPa	ISO 527-3
Modulus of elasticity MD	290	MPa	ISO 527-3
<b>Tensile test film</b>			
Strain at break MD	>200	%	ISO 527-3
Strain at break TD	>500	%	ISO 527-3
Coefficient of friction	1	-	ASTM D1894
Blocking	10	g	SABIC method
Re-blocking	30	g	SABIC method
<b>THERMAL PROPERTIES</b>			
Vicat Softening Temperature at 10 N (VST/A)	106	°C	ISO 306



## STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

## ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.