



# SABIC® LLDPE 121WJ

LINEAR LOW DENSITY POLYETHYLENE

### DESCRIPTION

121WJ is a high quality Linear Low Density Polyethylene TNPP free grade for blown film. It has excellent processability and films produced from this resin have good clarity, excellent puncture resistance, high tensile strength and good sealing characteristics. 121WJ contains slip and antiblock additive.

### TYPICAL APPLICATIONS

Ice bags, frozen food bags, produce bags, bread bags, carrier bags, garment bags, laminated films for food packaging.

### TYPICAL PROPERTY VALUES

Revision 20240709

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
190°C and 2.16 kg	1	g/10 min	ASTM D1238
Density	918	kg/m³	ASTM D1505
FORMULATION			
Slip agent	☑	-	-
Anti static agent	☑	-	-
MECHANICAL PROPERTIES			
Dart Impact Strength	100	g/µm	ASTM D1709
OPTICAL PROPERTIES			
Haze <sup>(1)</sup>	9	%	ASTM D1003
Gloss			
at 60°	90	-	ASTM D2457
FILM PROPERTIES			
Tensile Properties			
stress at break, MD	36	MPa	ASTM D882
stress at break, TD	30	MPa	ASTM D882
strain at break, MD	880	%	ASTM D882
strain at break, TD	830	%	ASTM D882
stress at yield, MD	9	MPa	ASTM D882
stress at yield, TD	8	MPa	ASTM D882
1% secant modulus, MD	200	MPa	ASTM D882
1% secant modulus, TD	180	MPa	ASTM D882
Puncture resistance	60	J/mm	SABIC method
Elmendorf Tear Strength			
MD	110	g	ASTM D1922
TD	450	g	ASTM D1922
THERMAL PROPERTIES			
Vicat Softening Temperature	100	°C	ASTM D1525

(1) Properties have been measured by producing 30 µm film with 2.5 BUR using 100% 121WJ.



## PROCESSING CONDITIONS

Typical processing conditions for 121WJ are:  
Melt temperature: 190 - 210°C, Blow up ratio: 2.0 - 3.0

## STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions, which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

