

SUPEER™ MLLDPE 7318BE

METALLOCENE C6 LLDPE

DESCRIPTION

SUPEER™ Metallocene Linear Low Density Polyethylene (mLLDPE) 7318BE is a metallocene ethylene-hexene copolymer. It has a good processability and performs well in a wide range of general purpose and high performance cast film applications. Films produced with this grade offer good impact strength, puncture resistance, sealing and optical properties.

SUPEER™ Metallocene Linear Low Density Polyethylene (mLLDPE) 7318BE is typically used for stretch and lamination films. Processing temperatures 210- 260 °C. Properties have been measured on cast film of 25 µm.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

Revision 20220923

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190 °C and 2,16 kg	3	dg/min	ASTM D1238
Density			
Density	918	kg/m³	ASTM D792
MECHANICAL PROPERTIES			
Dart Impact Strength ⁽¹⁾	24	g/µm	ASTM D1709
OPTICAL PROPERTIES			
Haze	4	%	ASTM D1003
FILM PROPERTIES			
Tear strength TD Elmendorf	17	g/µm	ASTM D1922
Tear strength MD Elmendorf	14	g/µm	ASTM D1922
Tensile test film			
Strain at break MD	650	%	ASTM D882
Strain at break TD	650	%	ASTM D882
Stress at break MD	42	MPa	ASTM D882
Stress at break TD	40	MPa	ASTM D882
Yield stress TD	9	MPa	ASTM D882
Yield stress MD	9	MPa	ASTM D882
THERMAL PROPERTIES			
DSC test			
melting point	122	°C	ASTM D3418
Vicat Softening Temperature			
at 10 N (VST/A)	103	°C	ISO 306

(1) Dart Impact F50 is measured via ASTM D1709 A



ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.