



SUPEER™ MLLDPE 8118L

METALLOCENE LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

SUPEER™ Metallocene Linear Low Density Polyethylene (mLLDPE) 8118L is an ethylene-octene copolymer produced via solution polymerization using metallocene catalyst. It performs well in a wide range of general purpose and high performance LLDPE blown film applications and have excellent processability. It contains slip and antiblock additives.

TYPICAL APPLICATIONS

Lamination film, liquid pouch, heavy duty bag, industrial liner, agriculture film, stretch hood, surface protective film.

TYPICAL PROPERTY VALUES

Revision 20201102

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	1.1	g/10 min	ASTM D1238
Density	918	kg/m³	ASTM D1505
FORMULATION			
Slip agent	☑	-	-
Anti block agent	☑	-	-
OPTICAL PROPERTIES			
Haze	10	%	ASTM D1003
FILM PROPERTIES			
Tensile test film			
stress at break, MD	54	MPa	ASTM D882
stress at break, TD	54	MPa	ASTM D882
elongation at break, MD	630	%	ASTM D882
elongation at break, TD	730	%	ASTM D882
stress at yield, MD	12	MPa	ASTM D882
stress at yield, TD	11	MPa	ASTM D882
1% secant modulus, MD	140	MPa	ASTM D882
1% secant modulus, TD	156	MPa	ASTM D882
Dart Impact F50	1000	g	ASTM D1709
Elmendorf Tear Strength ⁽¹⁾			
MD	14	g/μm	ASTM D1922
TD	22	g/μm	ASTM D1922
THERMAL PROPERTIES			
Melting Point	~115	°C	SABIC method

(1) Properties have been measured by producing 50 μm film with 2.5 BUR using 100% SUPEER™ 8118.

PROCESSING CONDITIONS

Typical processing conditions for SUPEER™ 8118L are:
Barrel temperature: 180 - 200°C, Blow up ratio: 2.0 - 3.0



FOOD REGULATION

Please contact the local Sales / Technical representative for details.

STORAGE AND HANDLING

The resin should be stored in a manner to prevent a direct exposure to sunlight and / or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions that may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

