



## Luban DNDC-7152

### Medium Density Polyethylene

#### Description

Luban DNDC-7152 Medium Density Polyethylene (MDPE) grade is a hexene copolymer with narrow molecular weight distribution. This grade is intended for use in rotational molding applications such as indoor storage containers.

#### Application

Roto-molded loft tanks (water), agriculture tanks, industrials pallets, trash containers, chemical shipping drums, water park slides

#### Properties (Typical Values)

Property	Unit	Test method	Value
Melt Index (190°C/2.16 kg)	g/10 min	ASTM D1238	3.5
Density	g /cm <sup>3</sup>	ASTM D792	0.939
Environmental Stress-Cracking Resistance 122°F (50°C), 100% Igepal, F50	hr	ASTM D1693 <sup>1</sup>	>1000
1% Secant Modulus	MPa	ASTM D638	550
Tensile stress at yield	MPa	ASTM D638	17
Tensile stress at break	MPa	ASTM D638	19
Tensile elongation at break	%	ASTM D638	660
Brittleness Temperature	°C	ASTM D746	<-100

<sup>1</sup> Tested on 1.9 mm specimen, slit

**Note:** These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.



## Luban DNDC-7152

### Medium Density Polyethylene

#### Storage and Handling

Luban DNDC-7152 must be protected from direct sunlight and should be stored in a shaded and completely dry area. During handling and processing, the material should be kept in a well-ventilated area to prevent the accumulation of dust and fumes. Contact with strong oxidizers, excessive heat, sparks or open flame should be avoided as this could initiate the degradation process and consequently impact the quality of the material.

#### Safety

Luban DNDC-7152 is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

#### Food Contact

Luban DNDC-7152 meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

#### Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: Mar. 2020

#### Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.