



LEXANT™ FR RESINS BFL2015

REGION EUROPE

DESCRIPTION

LEXAN BFL2015 Polycarbonate (PC) is an injection moldable non-chlorinated/brominated flame retardant grade that is 15% glass fiber filled and has improved flow. It has a UL94 V0@1.5mm rating and is available in various opaque color options.

TYPICAL PROPERTY VALUES

Revision 20200730

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	92	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	91	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3.5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	4	%	ASTM D638
Tensile Modulus, 5 mm/min	5330	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	156	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	4600	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	103	MPa	ISO 527
Tensile Stress, break, 50 mm/min	100	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.6	%	ISO 527
Tensile Strain, break, 50 mm/min	4.3	%	ISO 527
Tensile Modulus, 1 mm/min	4950	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	150	MPa	ISO 178
Flexural Modulus, 2 mm/min	4280	MPa	ISO 178
IMPACT			
Charpy Impact, unnotched, 23°C	67	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	75	kJ/m ²	ISO 179/2C
Izod Impact, notched, 23°C	78	J/m	ASTM D256
Izod Impact, notched, -30°C	N/A	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	61	J	ASTM D3763
Izod Impact, unnotched 80°10'3 +23°C	80	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10'3 -30°C	80	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10'3 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'3 -30°C	7	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'3 sp=62mm	8	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10'3 sp=62mm	6	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10'3 sp=62mm	100	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10'3 sp=62mm	100	kJ/m ²	ISO 179/1eU
Charpy Impact, notched, 23°C	12	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	8	kJ/m ²	ISO 179/2C
THERMAL			
Vicat Softening Temp, Rate B/50	148	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	145	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	141	°C	ASTM D648



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -30°C to 30°C, flow	4.E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	4.E-05	1/°C	ASTM D696
CTE, 23°C to 80°C, flow	4.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	4.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSESO	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	149	°C	ISO 306
Vicat Softening Temp, Rate B/120	150	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	132	°C	ISO 75/Af
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.23	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.5	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.5	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.2 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	6.5	g/10 min	ASTM D1238
Density	1.3	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	6	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 1.6 mm	20	kV/mm	ASTM D149
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Relative Permittivity, 1 MHz	3.1	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.02	-	IEC 60250
Dissipation Factor, 1 MHz	0.01	-	IEC 60250
Comparative Tracking Index	150	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.2	-	IEC 60250
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Oxygen Index (LOI)	38	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	290 – 320	°C	
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	290 – 320	°C	
Middle - Zone 2 Temperature	280 – 310	°C	
Rear - Zone 1 Temperature	270 – 300	°C	
Hopper Temperature	60 – 80	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	80 – 120	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

