



LEXANT™ RESIN HF3510R

REGION AMERICAS

DESCRIPTION

LEXANT™ HF3510R resin is a 39 MFR polycarbonate, MVR of 34. Mold release. Easy processing. Suitable for automotive applications, including bezels. Available only in opaque colors.

TYPICAL PROPERTY VALUES

Revision 20230321

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	58	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D638
Tensile Modulus, 50 mm/min	2400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	100	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	690	J/m	ASTM D256
Izod Impact, notched, -30°C	55	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	66	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	4	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	12	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
Izod Impact, notched 80*10*3 +23°C	55	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	11	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	55	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	11	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	139	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	135	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	124	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.2E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.8E-05	1/°C	ASTM E831



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, xflow	7.8E-05	1/°C	ISO 11359-2
Thermal Conductivity	0.2	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	7.0E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	139	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	130	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	122	°C	ISO 75/Af
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	133	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	121	°C	ISO 75/Ae
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/ 1.2 kgf	39	g/10 min	ASTM D1238
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.3	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Melt Volume Rate, MVR at 300°C/ 1.2 kg	36	cm ³ / 10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	265 – 290	°C	
Front - Zone 3 Temperature	270 – 295	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	250 – 270	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.