



SABIC® PPCOMPOUND 19T1020U

PP COMPOUND MINERAL FILLED

DESCRIPTION

SABIC® PPcompound 19T1020U is a general purpose, talcum filled grade. This homopolymer polypropylene compound is long term heat and uv stabilized, making it very suitable for example for E&E applications. This compound exhibits high flow and is suitable for injection molding applications.

IMDS ID: 163255030

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	18	dg/min	ISO 1133
Density ⁽¹⁾	1050	kg/m ³	ISO 1183
Filler content	20	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	0.95	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile			
Tensile modulus	3200	MPa	ISO 527/1A
stress at yield	36	MPa	ISO 527/1A
stress at break	32	MPa	ISO 527/1A
strain at break	10.5	%	ISO 527/1A
Flexural test			
Flexural modulus	3200	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	2.0	kJ/m ²	ISO 180/1A
at 0 °C	1.5	kJ/m ²	ISO 180/1A
at -20 °C	1.0	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	73	°C	ISO 75
at 0.45 MPa (HDT/B)	128	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	58	µm/mK	ISO 11359-2
FLAMMABILITY PROPERTIES			
GWFI			
3.0mm	750	°C	IEC 60695-2-12

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break



STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

