



SABIC® PPCOMPOUND 31T1010

PP COMPOUND MINERAL FILLED
REGION AMERICAS

DESCRIPTION

SABIC® PPcompound 31T1010 is a 10% talc-filled polypropylene copolymer for general purpose applications.

TYPICAL PROPERTY VALUES

Revision 20211207

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	23	MPa	ISO 527
Tensile Stress, break, 50 mm/min, 1A	14	MPa	ISO 527
Tensile Strain, break, 50 mm/min	51	%	ISO 527
Tensile Modulus, 1 mm/min	1620	MPa	ISO 527
Flexural Modulus, 2 mm/min, 64mm span	1700	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*3 +23°C	9	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 0°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -20°C	6	kJ/m ²	ISO 180/1A
THERMAL			
CLTE, -30C to 100°C, flow	84	µm/mK	ISO 11359-2
HDT 0.45 MPa, 80*10*4mm, Cut	107	°C	ISO 75-1&2
HDT 1.8 MPa, 80*10*4mm, Cut	58	°C	ISO 75-1&2
PHYSICAL			
Filler Content	10	%	ASTM D229
Mold Shrinkage, flow, 24 hrs	1.4	%	ASTM D955
Density	0.96	g/cm ³	ISO 1183
Melt Flow Rate, 230°C/2.16 kg	13	g/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	80 – 100	°C	
Drying Time	2 – 4	Hrs	
Melt Temperature	210 – 270	°C	
Nozzle Temperature	210 – 270	°C	
Front - Zone 3 Temperature	210 – 270	°C	
Middle - Zone 2 Temperature	200 – 250	°C	
Rear - Zone 1 Temperature	190 – 230	°C	
Mold Temperature	15 – 60	°C	
Back Pressure	1 – 1.5	MPa	

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

