



## Luban DFDC-7050

### Linear Low Density Polyethylene

#### Description

Luban DFDC-7050 is a butene LLDPE grade designed for the blown film process, offering high gloss and excellent draw down. Films made from DFDC-7050 resin have very good tensile and toughness properties.

Additives:

- Anti-block: High
- Slip: Medium
- Thermal Stabilizer

#### Application

Agricultural Film, bag in box, food packaging films, FFS packaging films, garment bags, liner bags, multi-layer packaging films, cast film

#### Properties (Typical Values)

| Property                           | Unit               | Test method | Value*  |
|------------------------------------|--------------------|-------------|---------|
| Melt Index (190°C/2.16 kg)         | g/10 min           | ASTM D1238  | 2       |
| Density                            | g /cm <sup>3</sup> | ASTM D792   | 0.918   |
| Tensile stress at yield (MD/TD)    | MPa                | ASTM D882   | 11/10   |
| Tensile stress at break (MD/TD)    | MPa                | ASTM D882   | 49/29   |
| Elongation at break (MD/TD)        | %                  | ASTM D882   | 600/800 |
| Secant modulus – 1% secant (MD/TD) | MPa                | ASTM D882   | 190/220 |
| Dart Drop Impact                   | g                  | ASTM 1709A  | 66      |
| Elmendorf tear strength (MD/TD)    | g                  | ASTM D1922  | 85/400  |
| Gloss (45°)                        |                    | ASTM D2457  | 76      |
| Haze                               | %                  | ASTM D1003  | 4.4     |

\* The film properties have been measured on 25.4 µm (1 mil) thick film (Blow-up ratio: 2.5). Optical film properties have been measured on a 25.4 µm (1 mil) thick film (without anti-block) with addition of 10% LDPE at the same conditions.

**Note:** These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.



## Luban DFDC-7050

### Linear Low Density Polyethylene

#### Storage and Handling

Luban DFDC-7050 must be protected from direct sunlight and should be stored in a shaded and completely dry area. During handling and processing, the material should be kept in a well-ventilated area to prevent the accumulation of dust and fumes. Contact with strong oxidizers, excessive heat, sparks or open flame should be avoided as this could initiate the degradation process and consequently impact the quality of the material.

#### Safety

Luban DFDC-7050 is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

#### Food Contact

Luban DFDC-7050 meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

#### Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: Mar. 2020

#### Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.