



# SABIC® PS 155

## GENERAL PURPOSE POLYSTYRENE FOR FOAM EXTRUSION

### DESCRIPTION

General purpose Polystyrene PS 155 is manufactured by continuous mass polymerization of styrene monomer. It is a crystal-like, hard and brittle polymer with medium flow and good tensile and flexural strength. It has high vicat and heat deflection temperatures.

### TYPICAL PROPERTY VALUES

Revision 20260305

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
@ 200°C & 5 kg <sup>(1)</sup>	7	g/10 min	ASTM D 1238
<b>Load Density@ 23°C</b>	1050	kg/m <sup>3</sup>	ASTM D792
<b>Bulk Density (Method B)</b>	600	kg/m <sup>3</sup>	ASTM D 1895
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile Strength</b>	45	MPa	ASTM D638
<b>Tensile Elongation</b>	2	%	ASTM D638
<b>Tensile modulus</b>	2990	MPa	ASTM D638
<b>Flexural Strength</b>	66	MPa	ASTM D790
<b>Flexural Modulus</b>	3627	MPa	ASTM D790
<b>Izod impact notched at 23 °C</b>	16	J/m	ASTM D256A
<b>Rockwell Hardness</b>			
L-Scale <sup>(2)</sup>	93	-	ASTM D785
M-Scale	60	-	ASTM D785
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Point, (Rate A/50°C)</b>	102	°C	ASTM D1525
<b>Heat Deflection Temperature (Method B, 455 KPa, Annealed)</b>	100	°C	ASTM D648
<b>Flammability Rating, UL 94</b>			
@ 1.3 mm and 3 mm (natural color) <sup>(1)</sup>	MB	Rate	-

(1) Typical values; not to be construed as specification limits.

(2) Based on Injection molded specimens.

### APPLICATIONS

It is recommended for extrusion purposes. It can be used for foam extrusion application such as building insulation.

### PROCESSING CONDITIONS

Typical temperature (°C) profile for PS 155:

Throat Ambient, Feed 185°C, Transition 200°C, Metering 220°C and Die 230°C

### FOOD REGULATION

PS 155 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.



## STORAGE AND HANDLING

Polystyrene resin should be stored to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PS resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

